

ANHYDROUS NICKEL CHLORIDE



HIGH PURITY AND RELIABILITY

Benefiting from a unique production process at ERAMET's Le Havre-Sandouville refinery, ERAMET's anhydrous nickel chloride was launched in 2008 as the first anhydrous nickel chloride produced in a western country.

Consistency and high purity makes ERAMET's anhydrous nickel chloride the ideal long-term choice for applications requiring an anhydrous environment such as catalyst production and electronics.

ANHYDROUS NICKEL CHLORIDE

SPECIFICATIONS

	Typical	Guaranteed
Nickel	45.3 %	44.8 – 45.3 %
Water content	< 0.3 %	< 1 %
Iron	< 0.0005 %	< 0.002 %
Cobalt	< 0.0005 %	< 0.002 %
Copper	< 0.001 %	< 0.002 %
Arsenic	< 0.001 %	< 0.002 %
Lead	< 0.0002 %	< 0.001 %
Cadmium	< 0.0002 %	< 0.001 %
Zinc	< 0.0005 %	< 0.001 %

REGULATIONS

ERAMET's Anhydrous nickel chloride is produced and sold in accordance with the REACH European Regulation (EC N° 1907/2006) and complies with the requirements of the European Union.

STANDARD PACKAGING

Big Bags

- ERAMET's Anhydrous Nickel Chloride is available in big bags of 200 kg.
- Big bags are sold on an ISPM 15-certified CP3 pallet, whose dimensions are 1114 (L) x 1114 (W) mm, and are wrapped in a protective polyethylene film.



PACKAGING ON REQUEST

- Packing in 10kg bags is also available upon request.
- Each pallet holds 40 bags of 10 kg each placed in a protective cardboard box trapped to the pallet. Two cardboards boxes are strapped to the pallet. All pallets are ISPM 15 compliant.

Pallet dimensions: 1200 (L) x 1000 (W) mm

Net weight: 800 kg

Gross weight: 835 kg



Contact and information: info.nickel@erametgroup.com - www.eramet.com



ERAMET